

Hard Wax Oil

PRODUCT FEATURES

- Oxidative hardening Hard Wax Oil based on renewable natural ingredients such as pine resin oil, waxes and linseed oil
- Suitable for all indoor wood types and surfaces, floors furniture and internal woodwork
- Gives a water- and dirt repellent protective surface
- High resistance to wear and tear
- Easy and quick to work with
- No visible overlaps

PREPARATION

Sand the floor down to bare wood, finishing with a sanding screen, grit 100. Arboritec Hard Wax Oil can also be applied on pre oiled surfaces. In this case apply a very thin layer.

APPLICATION

Arboritec Hard Wax Oil should be kept between 15-25°C when applied. Shake the can thoroughly.

Arboritec Hard Wax Oil is applied with a hard wax brush or a short hair roller in a thin and even layer. Let it dry for approximately 2 hours. If the surface gets rough due to grain raise, lightly sand it with a screen grit 120 and carefully remove any sanding dust.

Apply a thin second layer and let it dry for at least 24 hours. It is very important that the oil is not applied too thickly.

The gloss level can be adjusted by buffing.

Note! Oil saturated cloths and pads can self-ignite. Store used materials in water or in closed containers.

The trowel and other tools can be cleaned with white spirit before the oil has hardened.

MAINTENANCE

Dry cleaning is recommended on all oiled surfaces. If necessary clean with Arboritec Cleaner. Do not leave water on the floor. If the floor is heavily worn, maintain with Arboritec Satin Maintenance Oil. If this does not give the desired result, sand lightly with a sanding screen grit 120 and apply a fresh layer of Arboritec Hard Wax Oil.

HEALTH AND ENVIRONMENT

Arboritec Hard Wax Oil is not classified under the C.H.I.P. regulations. Use the normal care due when handling chemical products. Ensure good ventilation. Use protective goggles and gloves if there is any risk of splashing. If the product comes into contact with your skin, wash it off with soap and water. If the product gets into your eyes, rinse with a generous amount of water. For further information see Material Safety Data Sheet



TECHNICAL DATA

Contents:	Urethane-modified pine resin oil linseed oil, waxes
Usage:	1 litre for 20-30 m ² /coat depending on wood species and wood condition
Solids content:	45%
Working temp.:	+15-25°C
Drying time:	1st coat 2 hours; 2nd coat 24 hours
Storage:	Best before 2 years after production at max 40°C in unopened can. Once the can is opened the content might start hardening when stored a longer time. Store upside down. Keep out of the reach of children. Not sensitive to frost.
Package:	5 litre metal can. Pallet: 600l or 120 cans 1-liter metal can. Pallet: 600l

This Arboritec Product Sheet is intended for advice only. The figures apply to normal conditions, which may vary due to means of application, temperature etc. We retain the right to make changes and amendments without prior notice.

A safety data sheet is available for professional users on request. Keep out of the reach of children.

For technical advice: Contact your distributor or Arboritec Technical Service at +46 303 56330

The information and recommendations in this data sheet are guidelines for application and are not to be construed as a guarantee. In all cases it is the responsibility of the user to determine if the product is suitable for the purpose, and complete a successful application. Arboritec can only guarantee the delivered product. If the user is in doubt we would recommend a preliminary onsite test. Please ensure you have read and understood all information on the labels and in the safety data sheets before using this product.

Rev 13-04-25. This data sheet replaces all previous versions.